



Torlon® 4645

polyamide-imide

Torlon 4645, an injection-moldable, wear-resistant grade of polyamide-imide (PAI), has been formulated to give outstanding wear resistance in lubricated wear applications.

Torlon PAI has the highest strength and stiffness of any thermoplastic up to 275°C (525°F). It has outstanding resistance to wear, creep and chemicals.

Potential applications for Torlon 4645 polyamide-imide include thrust washers, seal rings, sliding vanes, bobbins, bushings, clutch rollers and pistons.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Additive	• Carbon Fiber + PTFE Lubricant		
Features	• Flame Retardant • Good Chemical Resistance • Good Creep Resistance • Good Wear Resistance	• High Heat Resistance • High Stiffness • High Temperature Strength • Low Friction	• Self Lubricating • Semi Conductive
Uses	• Automotive Applications • Bearings	• Bobbins • Bushings	• Seals • Thrust Washer
RoHS Compliance	• Contact Manufacturer		
Forms	• Pellets		
Processing Method	• Injection Molding	• Machining	• Profile Extrusion

Physical	Typical Value	Unit	Test Method
Specific Gravity	1.57	g/cm ³	ASTM D792
Water Absorption (24 hr)	0.25	%	ASTM D570
Mechanical	Typical Value	Unit	Test Method
Tensile Modulus	18600	MPa	ASTM D638
Tensile Strength	114	MPa	ASTM D638
Tensile Elongation (Break)	0.80	%	ASTM D638
Flexural Modulus	12400	MPa	ASTM D790
Flexural Strength	154	MPa	ASTM D790
Compressive Strength	157	MPa	ASTM D695
Shear Strength			ASTM D732
23°C	85.5	MPa	
150°C	60.7	MPa	
Coefficient of Friction			ASTM D1894
-- 1	0.070		
-- 2	0.090		
Wear Factor			ASTM D3702
Lubricated: 0.375 m/s, 6.9 MPa (75 fpm, 1000 psi)	1.60	in ³ ·min ⁻¹ ·lb ⁻¹	

Mechanical	Typical Value	Unit	Test Method
Lubricated: 4 m/s, 5.2 MPa (800 fpm, 750 psi)	0.300	in ³ ·min ⁻¹ - 10/ft·lb·hr	

Impact	Typical Value	Unit	Test Method
Notched Izod Impact	37	J/m	ASTM D256
Unnotched Izod Impact	110	J/m	ASTM D256

Thermal	Typical Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	281	°C	ASTM D648
Coefficient of Linear Thermal Expansion	0.000014	cm/cm/°C	ASTM D696

Injection	Typical Value	Unit
Drying Temperature	177	°C
Drying Time	3.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	304	°C
Nozzle Temperature	371	°C
Mold Temperature	199 to 216	°C
Back Pressure	6.89	MPa
Screw Speed	50 to 100	rpm
Screw L/D Ratio	18.0:1.0 to 24.0:1.0	

Injection Notes

Minimum drying times are: 3 hours at 350°F (177°C), 4 hours at 300°F (149°C), or 16 hours at 250°F (121°C).

Compression Ratio between 1:1 and 1.5:1

Begin hold pressure at a high setting 6,000-8,000 psi (41.37-55.16 MPa), for several seconds, then drop off to 3,000-5,000 psi (20.69-34.48 MPa), for the duration of the hold pressure sequence.

Molded parts must be post cured.

Notes

Typical properties: these are not to be construed as specifications.

¹ Lubricated: 4 m/s, 5.2 MPa (800 fpm, 750 psi)

² Lubricated: 0.25 m/s, 6.9 MPa (75 fpm, 1000 psi)

For assistance with an emergency involving products of Solvay Advanced Polymers, such as a spill, leak, fire, or explosion, call day or night:

Emergency Health Information

USA +1.800.621.4590

International +1.770.772.8577

Emergency Spill Information

USA +1.800.424.9300 / +1.703.527.3887

(CHEMTREC)

Europe +44 208.762.8322 (CARECHEM)

China +86.10.5100.3039

All other Asian countries +65.633.44.177

For additional product information, technical assistance, and Material Safety Data Sheets (MSDS), call:

USA + 1.800.621.4557/ +1.770.772.8760

Europe +49.211.5135.9000

Japan +81.3.5425.4300

China & Southeast Asia +86.21.5080.5080

World Headquarters

Solvay Advanced Polymers, L.L.C.

4500 McGinnis Ferry Road

Alpharetta, GA 30005 USA

+1.800.621.4557 (U.S.A.)

+1.770.772.8760

SOLVAY
Advanced Polymers



MORE PLASTICS WITH MORE PERFORMANCE™

Solvay Advanced Polymers has many locations around the world. Please visit our website for the office nearest you, or email advancedpolymers@solvay.com for assistance. www.solvayadvancedpolymers.com

Material Safety Data Sheets (MSDS) for products of Solvay Advanced Polymers are available upon request from your sales representative or by emailing us at advancedpolymers@solvay.com. Always consult the appropriate MSDS before using any of our products.

Property values for individual batches will vary within specification limits. Unless otherwise noted, values shown are typical for uncolored resin; colorants may alter values. For Preliminary Data Sheets, values are typical of limited production and specifications are not yet established.

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Advanced Polymers, LLC nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this information or its use. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for implantable medical devices; Solvay Advanced Polymers does not allow or support the use of any other products in any implant applications. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The use of this product resides on the determination of the customer not Solvay Advanced Polymers. The customer must determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Advanced Polymers reserves the right to make additions, deletions, or modifications to the information at any time without prior notification.

All trademarks and registered trademarks are the property of Solvay Advanced Polymers, LLC, an affiliate of Solvay SA.

© 2011 Solvay Advanced Polymers, LLC. All rights reserved.