



DRAKE PLASTIC'S HT PROPERTY COMPARISON

HT 1.00" ROD

	DRAKE HT RESULTS Batch:VPB1585 Run: 082509	ACTUALS FROM VICTREX HT Batch: VPB1585 COC
TENSILE STRESS (psi)	16,911	16,969 (117 MPa)
TENSILE ELONGATION	65.55%	63%
FLEX MODULUS (psi)	636,816	667,174 (4.6 GPa)



HT 2.625" ROD

	DRAKE HT RESULTS Batch:VPB4508 Run: 081111	ACTUALS FROM VICTREX HT Batch: VPB4508 COC
TENSILE STRESS (psi)	16,491	15,954 (110 MPa)
TENSILE ELONGATION	54.71%	70.60%
FLEX MODULUS (psi)	664,031	623,662 (4.3 GPa)

