

AvaSpire® AV-621

polyaryletherketone

AvaSpire® AV-621 is an unreinforced polyaryletherketone (PAEK) that offers improved ductility and impact strength relative to PEEK while retaining most of the key performance attributes of PEEK. The AV-621 grade is the low melt flow (higher molecular weight) analog of the medium flow grade AvaSpire® AV-651 that is tailored primarily for injection molding applications as well as film extrusion. AvaSpire® AV-621 resin is suited for a variety of processing methods including compression molding, stock shape extrusion, as well as injection molding.

AV-621 has been formulated for applications requiring a balance of chemical resistance and mechanical strength

along with good part aesthetics, thereby bridging the performance gaps within the ultra polymers space. These and other properties make this resin well-suited for applications in healthcare, transportation, semiconductor, electronics, chemical processing, and other industries.

AvaSpire® AV-621 is easily fabricated using conventional thermoplastic melt processing techniques and standard equipment. The resin has a uniform opaque appearance with a beige color similar to that of PEEK.

- AvaSpire® AV-621 NT

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Ductile • Fatigue Resistant • Flame Retardant	• Good Chemical Resistance • Good Dimensional Stability • Good Impact Resistance	• High Heat Resistance
Uses	• Bearings • Bushings	• Connectors • Medical/Healthcare Applications	• Oil/Gas Applications • Semiconductor Molding Compounds
RoHS Compliance	• RoHS Compliant		
Appearance	• Beige		
Forms	• Pellets		
Processing Method	• Extrusion Blow Molding • Fiber (Spinning) Extrusion • Film Extrusion	• Injection Blow Molding • Injection Molding • Machining	• Profile Extrusion • Thermoforming • Wire & Cable Extrusion

Physical	Typical Value	Unit	Test method
Specific Gravity	1.29		ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage ¹			ASTM D955
Flow : 3.18 mm	0.70 to 0.90	%	
Across Flow : 3.18 mm	1.1 to 1.3	%	
Water Absorption (24 hr)	0.20	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus			
-- ²	2900	MPa	ASTM D638
--	3100	MPa	ISO 527-2/1A/1

AvaSpire® AV-621

polyaryletherketone


Mechanical	Typical Value	Unit	Test method
Tensile Stress			
Yield	87.0	MPa	ISO 527-2/1A/50
-- ²	84.0	MPa	ASTM D638
Tensile Elongation			
Yield ³	6.0	%	ASTM D638
Yield	5.7	%	ISO 527-2/50
Break ³	> 40	%	ASTM D638
Break	> 40	%	ISO 527-2/1A/50
Flexural Modulus			
--	3100	MPa	ASTM D790
--	3000	MPa	ISO 178
Flexural Strength			
--	122	MPa	ASTM D790
--	106	MPa	ISO 178
Compressive Strength	111	MPa	ASTM D695
Shear Strength	81.0	MPa	ASTM D732
Poisson's Ratio	0.39		ASTM E132
Impact	Typical Value	Unit	Test method
Notched Izod Impact			
--	100	J/m	ASTM D256
--	7.6	kJ/m ²	ISO 180
Unnotched Izod Impact	No Break		ASTM D4812 ISO 180
Hardness	Typical Value	Unit	Test method
Rockwell Hardness (M-Scale)	93		ASTM D785
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load ⁴			ASTM D648
1.8 MPa, Annealed, 3.20 mm	187	°C	
Glass Transition Temperature	158	°C	ASTM D3418
Peak Melting Temperature	340	°C	ASTM D3418
CLTE - Flow (-50 to 50°C)	4.7E-5	cm/cm/°C	ASTM E831
Specific Heat			DSC
50°C	1450	J/kg/°C	
200°C	2000	J/kg/°C	
Thermal Conductivity	0.20	W/m/K	ASTM E1530
Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.9E+17	ohms	ASTM D257
Volume Resistivity	6.2E+17	ohms·cm	ASTM D257
Dielectric Strength			ASTM D149
0.0500 mm, Amorphous Film	190	kV/mm	
3.00 mm	17	kV/mm	

AvaSpire® AV-621


polyaryletherketone

Electrical	Typical Value	Unit	Test method
Dielectric Constant			ASTM D150
60 Hz	3.07		
1 kHz	3.12		
1 MHz	3.10		
Dissipation Factor			IEC 60250
60 Hz	1.0E-3		
1 kHz	1.0E-3		
1 MHz	4.0E-3		
Flammability	Typical Value	Unit	Test method
Flame Rating			UL 94
0.800 mm	V-0		
1.60 mm	V-0		
Oxygen Index	34 %		ASTM D2863
Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec ⁻¹)	410	Pa·s	ASTM D3835
Injection	Typical Value	Unit	
Drying Temperature	150	°C	
Drying Time	4.0	hr	
Rear Temperature	355	°C	
Middle Temperature	365	°C	
Front Temperature	370	°C	
Nozzle Temperature	375	°C	
Processing (Melt) Temp	365 to 390	°C	
Mold Temperature	150 to 180	°C	
Injection Rate	Fast		
Screw Compression Ratio	2.0:1.0 to 3.0:1.0		

Isothermal Stress vs. Strain (ISO 11403-1)



Viscosity vs. Shear Rate (ISO 11403-2)



AvaSpire® AV-621

polyaryletherketone

Notes

Typical properties: these are not to be construed as specifications.

¹ 5" x 0.5" x 0.125"

² 50 mm/min

³ 51 mm/min

⁴ 2 hours at 200°C

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2015 Solvay Specialty Polymers. All rights reserved.

